

Erratum

In the paper "Thermodynamic Limitation of Self-dessiccation" by O.M. Jensen which appeared in Vol. 25(1), pp. 157-164 (1995), the following acknowledgement was omitted: This paper is based on a part of the author's Ph.D. work (5). Permissions to reproduce Figures no. 1 and 2 are kindly given by the American Concrete Institute and the Transportation Research Board, National Research Council, Washington, DC, respectively.

Erratum

In the paper entitled "The Influence of Polypropylene Fibers and Aggregate Grading on the Properties of Dry-Mix Shotcrete" by Ann Lamontagne and Michel Pigeon, which appeared in Vol. 25(2), pp. 293-298 (1995), there was a mistake in Table 4 (p. 296). It should have been presented as follows:

TABLE 4 - Tests on hardened shotcrete

Mixes	Compressive strength (MPa)	Drying shrinkage ⁽¹⁾ (μm/m)	Chloride permeability (C)	Air content (bubbles only) ⁽²⁾ (%)	Total air content (%)	Spacing factor (μm)	Permeable voids (%)	Scaling residues (kg/m ²)
CM1	34	761	4775	3,5	8,5	259	14,3	0,4
CM1-2f	32	928	12750	2,8	5,2	243	17,6	0,2
CM1-4f	30	810	8019	2,9	5,6	246	18,2	0,1
SM1	30	1147	1956	3,2	6,3	178	18,0	1,2
SM1-2f	39	821	963	3,7	6,4	235	16,7	2,5
SM1-4f	30	782	1220	2,8	5,3	235	19,7	2,2
SM0	37	878	2051	3,5	6,9	180	17,4	4,1
SM1	30	1147	1956	3,2	6,3	178	18,0	1,2
SM2	32	841	967	2,7	6,7	170	15,3	1,1
SM3	31	782	926	3,6	7,1	251	14,0	1,0
SF0	28	722	1423	2,7	9,0	204	17,4	3,5
SF1	33	798	1209	2,8	5,4	225	17,6	2,2
SG0	34	938	1043	3,1	5,6	221	13,2	0,5
SG1	30	689	810	3,1	4,4	190	15,6	1,0

(1) After 181 days of drying

(2) The spherical (entrained) air voids were counted separately from the compaction voids (which have an irregular shape)