

Erratum

Erratum to “Utilization of aluminum sludge and aluminum slag (dross) for the manufacture of calcium aluminate cement” [Ceram. Int. 35 (2009) 3381–3388]

E.M.M. Ewais^{a,*}, N.M. Khalil^b, M.S. Amin^c, Y.M.Z. Ahmed^a, M.A. Barakat^d

^a Refractory & Ceramic Materials Lab (RCML), Central Metallurgical Research and Development Institute (CMRDI),
P.O. Box 87, Helwan, 11421 Cairo, Egypt

^b Chemistry Department, Faculty of Science, Sebha University, Libya

^c Chemistry Department, Faculty of Science, Ain Shams University, Cairo, Egypt

^d Chemical & Electrochemical Metallurgy Laboratory, Research and Development Institute (CMRDI), P.O. Box 87, Helwan, 11421 Cairo, Egypt

Available online 31 March 2010

The publisher regrets that Table 2 published in the paper referenced above was incorrect.
Please see correct figure below.

Table 2
Composition of the mixes.

Mix no.	Green mix composition, wt.%			Chemical composition of the fired mixes, wt.%								
	Sludge	Aluminum slag (dross)	Aluminum oxide	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	CaO	MgO	MnO	Na ₂ O	K ₂ O
1	50	37.5	12.5	1.71	62.55	0.07	0.15	31.46	3.1	0.05	0.8	0.11
2	45	41.25	13.75	1.75	65.85	0.07	0.16	28.01	3.11	0.06	0.87	0.12
3	40	45	15	1.8	69.07	0.07	0.16	24.65	3.12	0.06	0.94	0.13
4	35	48.75	16.25	1.84	72.2	0.08	0.17	21.38	3.13	0.06	1	0.14

DOI of original article: [10.1016/j.ceramint.2009.06.008](https://doi.org/10.1016/j.ceramint.2009.06.008).

* Corresponding author. Tel.: +20 2 38621782; fax: +20 2 38621782.

E-mail address: dr_ewais@hotmail.com (E.M.M. Ewais).